

Test Number: 160705

Report Number: 26523T

Date of Issue: 29th April 2016

Page 1 of 2 Pages

FINAL REPORT FOR INDUSTRIAL PROCESSORS LTD

Clients Address: PO Box 36
Waitakere
Auckland 0614

Attention: Mr Ross Sutherland

Subject: **AGGREGATE TESTING**

Clients Instructions: Conduct the tests as detailed below on the aggregate sample supplied.

Test Methods: 1. NZS3111: 1986: Section
6: Particle Size Distribution – Dry Sieve Method
9: Determination of the Light Weight Particles

Date Sampled: Unknown

Date Received: 14th April 2016

Date of Test: April 2016

Description of Sample: **No.1 Washed Sand**

Source: Unknown

- Note:
- i. Sample received in its natural state.
 - ii. Aggregate sampled by unknown personnel using an unknown method.
 - iii. Sampling of aggregate is not covered by this report.

for STEVENSON LABORATORY LTDT. A. WHITMORE
IANZ APPROVED SIGNATORY

TEST RESULTS

Material:	No.1 Washed Sand	Test No.:	160705
Source:	Unknown	Date Sampled:	Unknown

TEST METHOD	RESULT	SPECIFICATION
Particle Size Distribution (Dry Sieve Method)	See below	See Below
Light Weight Particles	0.5%	-

SIEVE SIZE (mm)	26.5	19	13.2	9.5	6.7	4.75	2.36	1.18	.600	.425	.300	.150	.075
% PASSING SIEVE	-	-	-	-	-	-	100	100	71	29	10	2	1
MAXIMUM SPECIFIED LIMIT	-	-	-	-	-	-	-	-	-	-	-	-	-
MINIMUM SPECIFIED LIMIT	-	-	-	-	-	-	-	-	-	-	-	-	-
OVEN DRIED SAMPLE	Fineness Modulus: 2.17												

